



The Lattice and Thermal Radiation Conductivity of Thermal Barrier Coatings: Models and Experiments

Dongming Zhu and Charles M. Spuckler
Glenn Research Center, Cleveland, Ohio

NASA STI Program . . . in Profile

Since its founding, NASA has been dedicated to the advancement of aeronautics and space science. The NASA Scientific and Technical Information (STI) program plays a key part in helping NASA maintain this important role.

The NASA STI Program operates under the auspices of the Agency Chief Information Officer. It collects, organizes, provides for archiving, and disseminates NASA's STI. The NASA STI program provides access to the NASA Aeronautics and Space Database and its public interface, the NASA Technical Reports Server, thus providing one of the largest collections of aeronautical and space science STI in the world. Results are published in both non-NASA channels and by NASA in the NASA STI Report Series, which includes the following report types:

- **TECHNICAL PUBLICATION.** Reports of completed research or a major significant phase of research that present the results of NASA programs and include extensive data or theoretical analysis. Includes compilations of significant scientific and technical data and information deemed to be of continuing reference value. NASA counterpart of peer-reviewed formal professional papers but has less stringent limitations on manuscript length and extent of graphic presentations.
- **TECHNICAL MEMORANDUM.** Scientific and technical findings that are preliminary or of specialized interest, e.g., quick release reports, working papers, and bibliographies that contain minimal annotation. Does not contain extensive analysis.
- **CONTRACTOR REPORT.** Scientific and technical findings by NASA-sponsored contractors and grantees.

- **CONFERENCE PUBLICATION.** Collected papers from scientific and technical conferences, symposia, seminars, or other meetings sponsored or cosponsored by NASA.
- **SPECIAL PUBLICATION.** Scientific, technical, or historical information from NASA programs, projects, and missions, often concerned with subjects having substantial public interest.
- **TECHNICAL TRANSLATION.** English-language translations of foreign scientific and technical material pertinent to NASA's mission.

Specialized services also include creating custom thesauri, building customized databases, organizing and publishing research results.

For more information about the NASA STI program, see the following:

- Access the NASA STI program home page at <http://www.sti.nasa.gov>
- E-mail your question via the Internet to help@sti.nasa.gov
- Fax your question to the NASA STI Help Desk at 443-757-5803
- Telephone the NASA STI Help Desk at 443-757-5802
- Write to:
NASA Center for AeroSpace Information (CASI)
7115 Standard Drive
Hanover, MD 21076-1320



The Lattice and Thermal Radiation Conductivity of Thermal Barrier Coatings: Models and Experiments

Dongming Zhu and Charles M. Spuckler
Glenn Research Center, Cleveland, Ohio

Prepared for the
33rd International Conference and Exposition on Advanced Ceramics and Composites
sponsored by the American Ceramic Society
Daytona Beach, Florida, January 18–23, 2009

National Aeronautics and
Space Administration

Glenn Research Center
Cleveland, Ohio 44135

This work was sponsored by the Fundamental Aeronautics Program
at the NASA Glenn Research Center.

Level of Review: This material has been technically reviewed by technical management.

Available from

NASA Center for Aerospace Information
7115 Standard Drive
Hanover, MD 21076-1320

National Technical Information Service
5301 Shawnee Road
Alexandria, VA 22312

Available electronically at <http://gltrs.grc.nasa.gov>

The Lattice and Thermal Radiation Conductivity of Thermal Barrier Coatings: Models and Experiments

Dongming Zhu and Charles M. Spuckler
National Aeronautics and Space Administration
Glenn Research Center
Cleveland, Ohio 44135

Abstract

The lattice and radiation conductivity of $\text{ZrO}_2\text{-Y}_2\text{O}_3$ thermal barrier coatings was evaluated using a laser heat flux approach. A diffusion model has been established to correlate the coating apparent thermal conductivity to the lattice and radiation conductivity. The radiation conductivity component can be expressed as a function of temperature, coating material scattering, and absorption properties. High temperature scattering and absorption of the coating systems can be also derived based on the testing results using the modeling approach. A comparison has been made for the gray and nongray coating models in the plasma-sprayed thermal barrier coatings. The model prediction is found to have a good agreement with experimental observations.



Revolutionary Ceramic Coatings Greatly Impact Gas Turbine Engine Technology


- **Ceramic thermal and environmental barrier coating system development goals**
 - Meet engine temperature and performance requirements
 - Ensure long-term durability
 - Improve technology readiness
 - Develop design tools and lifing methodologies
- **Crucial for envisioned supersonic vehicles: reduced engine emission, improved efficiency and long-term supersonic cruise durability**



www.nasa.gov 1



Revolutionary Ceramic Coatings Impact Gas Turbine Engine Technology (Continued)




www.nasa.gov 2



Objectives

- Evaluate thermal conductivity and thermal radiation resistance of ceramic coatings at high temperatures (2700 to 3200 °F), under realistically thermal gradient conditions
- Facilitate the development advanced thermal and environmental barrier coatings
- Improve understanding of the coating thermal radiation performance




www.nasa.gov 3



NASA Steady-State Laser Heat-Flux Approach for Ceramic Coating Thermal Conductivity Measurements

- A uniform laser (wavelength 10.6 μm) power distribution achieved using integrating lens combined with lens/specimen rotation
- The ceramic surface and substrate temperatures measured by 8 μm and two-color pyrometers and/or by an embedded miniature thermocouple
- Thermal conductivity measured at 5 sec intervals in real time



www.nasa.gov 4




Ceramic Coating Thermal Conductivity Measurement Approach by the Laser High-Heat-Flux Testing

$$k_{\text{ceramic}}(t) = q_{\text{thru}} \cdot l_{\text{ceramic}} / \Delta T_{\text{ceramic}}(t)$$

Where

$$q_{\text{thru}} = q_{\text{delivered}} - q_{\text{reflected}} - q_{\text{radiated}} \quad \text{and} \quad \Delta T_{\text{ceramic}}(t) = T_{\text{ceramic-surface}} - T_{\text{metal-back}} - \int_0^{l_{\text{bond}}} \frac{q_{\text{thru}} \cdot dl}{k_{\text{bond}}(T)} - \int_0^{l_{\text{substrate}}} \frac{q_{\text{thru}} \cdot dl}{k_{\text{substrate}}(T)}$$




www.nasa.gov 5



Thermal Conductivity of Fully Dense Oxides


- The radiation conductivity component evaluated
- Significant conductivity increase due to increased radiation at high temperatures especially under thermal gradients



www.nasa.gov 6



Thermal Conductivity of Fully Dense Oxides (Continued)




www.nasa.gov 7



Evaluation of Lattice and Radiation Thermal Conductivity of TEBC Systems at High Temperatures

- ZrO_2 -8wt% Y_2O_3 /BSAS/mullite+20wt%BSAS/Si coating on SiC/SiC CMC substrate
- Conductivity determined by a steady-state laser heat-flux technique
- Coating surface radiation can contribute 5 to 15% total heat transfer at 1650 °C



www.nasa.gov 8



Radiative Diffusion Models

- The diffusion conduction equations

$$q_{total} = k_{cond} \frac{dT}{dx} + \frac{16\sigma \cdot n^2 \cdot T_{ave}^3}{3(a + \sigma_s)} \frac{dT}{dx} = \left(k_{cond} + \frac{16\sigma \cdot n^2 \cdot T_{ave}^3}{3(a + \sigma_s)} \right) \frac{dT}{dx}$$

$$k_{effective} = k_{cond} + \frac{16\sigma \cdot n^2 \cdot T_{ave}^3}{3(a + \sigma_s)} = k_{cond} + k_{rad}$$

q_{total} = Total heat flux

k_{cond} = Intrinsic lattice conductive thermal conductivity

k_{rad} = radiation thermal conductivity

$k_{effective}$ = effective thermal conductivity



σ = Stefan-Boltzman constant $5.6704 \times 10^{-8} \text{ W}/(\text{m}^2 \cdot \text{K}^4)$

n = Refractive index, 2.2

a = Absorption coefficient, cm^{-1}

σ_s = Scattering coefficient, cm^{-1}

\bar{T} = Average temperature of the material, K



Radiative Diffusion Models for Nongray Materials

- The diffusion conduction models established for nongray coating materials

- The diffusion conduction equations

Gray model

$$\begin{cases} q_{total} = k_{cond} \frac{dT}{dx} + \frac{16\sigma \cdot n^2 \cdot T_{ave}^3}{3(a + \sigma_s)} \frac{dT}{dx} = \left(k_{cond} + \frac{16\sigma \cdot n^2 \cdot T_{ave}^3}{3(a + \sigma_s)} \right) \frac{dT}{dx} \\ k_{effective} = k_{cond} + \frac{16\sigma \cdot n^2 \cdot T_{ave}^3}{3(a + \sigma_s)} = k_{cond} + k_{rad} \end{cases}$$

q_{total} = Total heat flux

k_{cond} = Intrinsic lattice conductive thermal conductivity

k_{rad} = radiation thermal conductivity

$k_{effective}$ = effective thermal conductivity

σ = Stefan-Boltzman constant $5.6704 \times 10^{-8} \text{ W}/(\text{m}^2 \cdot \text{K}^4)$

n = Refractive index, 2.2



a = Absorption coefficient, cm^{-1}

σ_s = Scattering coefficient, cm^{-1}

\bar{T} = Average temperature of the material, K

Nongray model


$$\begin{cases} q_{total} = \left[k + \frac{16\sigma \cdot n^2 \cdot T_{ave}^3}{3\kappa} \left[F_{0 \rightarrow \lambda_{avg}} T_{ave} - F_{0 \rightarrow \lambda_{avg}} T_{env} \right] \right] \frac{[T(0) - T(d)]}{d} \\ F_{0 \rightarrow \lambda T} = \frac{15}{\pi^4} \sum_{n=1}^{\infty} \left[\frac{e^{-\frac{\lambda T}{n}}}{n} \left(\zeta^3 + \frac{3\zeta^2}{n} + \frac{6\zeta}{n^2} + \frac{6}{n^3} \right) \right] \end{cases}$$





Evaluation of Lattice and Radiation Thermal Conductivity of 3000 °F Coating Systems


- Freestanding coatings and gray layer radiative diffusion assumption models



www.nasa.gov 11




Scattering Component of Plasma-Sprayed Coating Systems



www.nasa.gov 12



Radiation Conductivity Component of Ceramic Materials




www.nasa.gov 13



Evaluation of Radiation Flux Resistance of Oxide Coating Systems

— Preliminary results showed doped HfO_2 coatings had better radiation resistance



www.nasa.gov 14



Concluding Remarks

- **Laser heat-flux approach established for radiation thermal conductivity measurements and advanced coating development**
- **Lattice and radiation conductivity determined for dense materials and coatings**
- **The diffusion conduction models established for gray and nongray coating materials**
- **Scattering and absorption determined for coatings under realistic thermal gradients at high temperatures**
- **Advanced coatings promising in reducing radiation conductivity**

REPORT DOCUMENTATION PAGE				Form Approved OMB No. 0704-0188	
<p>The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.</p> <p>PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.</p>					
1. REPORT DATE (DD-MM-YYYY) 01-02-2010		2. REPORT TYPE Technical Memorandum		3. DATES COVERED (From - To)	
4. TITLE AND SUBTITLE The Lattice and Thermal Radiation Conductivity of Thermal Barrier Coatings: Models and Experiments				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S) Zhu, Dongming; Spuckler, Charles, M.				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER WBS 984754.02.07.03.16.03	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) National Aeronautics and Space Administration John H. Glenn Research Center at Lewis Field Cleveland, Ohio 44135-3191				8. PERFORMING ORGANIZATION REPORT NUMBER E-17012	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) National Aeronautics and Space Administration Washington, DC 20546-0001				10. SPONSORING/MONITOR'S ACRONYM(S) NASA	
				11. SPONSORING/MONITORING REPORT NUMBER NASA/TM-2010-215670	
12. DISTRIBUTION/AVAILABILITY STATEMENT Unclassified-Unlimited Subject Categories: 23, 24, and 27 Available electronically at http://gltrs.grc.nasa.gov This publication is available from the NASA Center for AeroSpace Information, 443-757-5802					
13. SUPPLEMENTARY NOTES					
14. ABSTRACT The lattice and radiation conductivity of ZrO_2 - Y_2O_3 thermal barrier coatings was evaluated using a laser heat flux approach. A diffusion model has been established to correlate the coating apparent thermal conductivity to the lattice and radiation conductivity. The radiation conductivity component can be expressed as a function of temperature, coating material scattering, and absorption properties. High temperature scattering and absorption of the coating systems can be also derived based on the testing results using the modeling approach. A comparison has been made for the gray and nongray coating models in the plasma-sprayed thermal barrier coatings. The model prediction is found to have a good agreement with experimental observations.					
15. SUBJECT TERMS Thermal conductivity; Coatings; Scattering; Absorption; Absorbents; Thermal radiation; Oxides					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT	18. NUMBER OF PAGES 15	19a. NAME OF RESPONSIBLE PERSON STI Help Desk (email: help@sti.nasa.gov)
a. REPORT U	b. ABSTRACT U	c. THIS PAGE U			19b. TELEPHONE NUMBER (include area code) 443-757-5802

